Commercial Vinyl

Centra 2021

Specifications:

















Domestic heavy

Commercial very heavy

Industrial heavy

Slip resistant

Dimensional stability

al Thermal resistance

Chemical resistant

ical Light

| | Centra 1 | Centra 2 |
|----------------------------|---------------------|---------------------|
| Level of use - | 23 – 34 - 43 | 33 - 42 |
| Total thickness - | 2.00 mm | 2.30 mm |
| Wear layer - | 0.70 mm | 0.60 mm |
| Wear layer PUR treatment - | HyperGuard+ | HyperGuard+ |
| Total weight - | 2543 g/m2 | 2200 g/m2 |
| Width - | 2 m | 2 m |
| Standard length - | 25 m | 30 m |
| Inflammability - | Bfl-S1 | Bfl-S1 |
| Slip resistance - | DS | DS |
| Slip restraint - | R10 | R10 |
| Residual indentation - | 0.05 mm | 0.20 mm |
| Furniture leg resistance - | Very good | Very good |
| Electrical resistance - | 10 ⁹ Ohm | 10 ⁹ Ohm |
| Dimensional stability - | 0.05 % | 0.10 % |
| Heat insulation - | 0.0080 (m2.K/W) | 0.0108 (m2.K/W) |
| Light fastness - | 6 | 6-7 |
| Underfloor heating - | Suitable | Suitable |
| Resistance to chemicals - | Very good | Very good |
| Warranty | 5 years | 5 years |

RUBBER MIGRATION: This is a condition that can cause vinyl to discolour. Migration occurs when latex or rubber products
such as shoes, rubber backed mats or rubber soled slippers come into contact with vinyl over a period of time. This is not a
manufacturing fault and therefore is not covered under our warranties.

Please contact us on 03 366 9839 to request any samples or other product details.

international flooring solutions

p 03 366 9839 e office@robertmalcolm.co.nz 59 Halwyn Drive, PO Box 914, Christchurch 8140, New Zealand robertmalcolm.co.nz

