



DIMENSIONS

| | |
|---------------------------|----------------------------|
| Length | 2050mm |
| Width | 240mm |
| Thickness | 9.5mm |
| Bevels | Genuine Bevel 4 sides |
| Number of panels per pack | 6 |
| m ² per pack | 2.952m ² |
| Joining system | Uniclic® 4 sides |
| Water damage warranty | 15-year waterproof surface |

FACTORY WARRANTY

| | METHOD | PARAMETERS | NORM REQUIREMENTS | QUICK-STEP VALUES |
|-------------|-----------------|-------------------------|-------------------------|---|
| Usage class | EN 13329 | | | Class 32 |
| Warranty | Residential use | See warranty conditions | See warranty conditions | Lifetime (33-year) Wear warranty |
| | | See warranty conditions | See warranty conditions | 15-year Waterproof Surface |
| | Commercial use | See warranty conditions | See warranty conditions | 5-year Waterproof Surface Wear warranty on Application |

GENERAL DATA

| | METHOD | PARAMETERS | NORM REQUIREMENTS | QUICK-STEP VALUES | |
|---|--------------------------|------------------------------|--|-----------------------|---------|
| Wear resistance | EN 13329 | | >4,000 cycles | With overlay Class 32 | |
| Wear class | EN 13329 | | AC4 | With overlay AC4 | |
| Impact resistance | EN 13329 | | IC2 | IC2 | |
| Scratch resistance | EN 438-2:25 | | Charge ≥ 3N | Charge ≥ 5N | |
| Effect of a castor chair | ISO 4918 (with underlay) | Type W (EN 12529) | 25,000 cycles | No change | |
| Thickness swelling | ISO 24336 | After 24hr immersion at 20°C | ≤ 18% | ≤ 12% | |
| | | | | | |
| Locking strength | ISO 24334 | F10.2 long side | ≥ 1 kN/m | ≥ 1 kN/m | |
| | | Fmax long side | | ≥ 1 kN/m | |
| | | Fs0.2 short side | ≥ 2 kN/m | ≥ 2 kN/m | |
| | | Fmax short side | | ≥ 2 kN/m | |
| Effect of furniture leg | EN 424 | | No damage shall be visible, when tested with foot type 0 | No visible Damage | |
| Surface soundness | EN 13329 | N/mm ² | ≥ 1.25 | ≥ 1.50 | |
| Static indentation | EN 24343 | Residual indentation | ≤ 0.05mm | No visible change | |
| Resistance to staining | EN 438 | Group 1, 2 | Class 5 | Class 5 | |
| | | Group 3 | Class 4 | Class 5 | |
| General appearance | EN 13329 | Height difference | ≤ 0.15mm | ≤ 0.10mm | |
| | | Opening between joints | ≤ 0.20mm | ≤ 0.10mm | |
| | | Cupping in the length | concave ≤ 0.50% | | ≤ 0.50% |
| | | | convex ≤ 1.0% | | ≤ 1.0% |
| | | Cupping in the width | concave ≤ 0.15% | | ≤ 0.15% |
| convex ≤ 0.20% | | | ≤ 0.20% | | |
| Dimensional variations after changes in relative humidity | EN 13329 | δl | δl average ≤ 0.9mm | ≤ 0.9mm | |
| | | δw | δw average ≤ 0.9mm | ≤ 0.9mm | |
| Light fastness | EN ISO 105 B02 | Blue reference | Class > 6 | Class 8 | |





OTHER TECHNICAL DATA

| | METHOD | PARAMETERS | NORM REQUIREMENTS | QUICK-STEP VALUES |
|-------------------|-------------|------------|-------------------|-------------------|
| Burning cigarette | EN 438-2:30 | | Class 4 | Class 5 |

ENVIRONMENT, SAFETY & HEALTH

| | METHOD | PARAMETERS | NORM REQUIREMENTS | QUICK-STEP VALUES |
|-----------------------|---------------|------------------------|---------------------------------------|---|
| Formaldehyde emission | EN 717-1 | ppm (large chamber) | E1 < 0.1 | < 0.01 |
| Anti-static | EN 1815 | | ≤ 2.0 kV | ≤ 2.0 kV |
| Reaction to fire | AS/ISO 9239.1 | Class | | 10.8kW/m ² /Smoke 4% |
| Thermal resistance | EN 12996:2001 | m ² K/W | | 0.065m ² K/W |
| Floor heating | | On Quick-Step underlay | See special installation instructions | Suitable |
| Slip resistance | AS 4586 | Pendulum test | | P2 - Desert/Valley Oak surfaces P3 - Woodland Oak Surfaces |

CERTIFICATES

| | | | | |
|----------------------|--|--|--|---------------|
| U-zeichen | | | | z-156.606-996 |
| AFFSET | | | | A+ |
| Nordic ecolabel | | | | 30290001 |
| PEFC | | | | PEFC/07-32-37 |
| Singapore Greenlabel | | | | 035-098-1422 |
| M1 | | | | |

